

PIPE

Steel

Structural/Tested Pipe

Schedule 40

Size Inches	Outside Diameter	Inside Diameter	Wall Thickness	LBS. Per Ft.
1/8	.405	.269	.068	.24
1/4	.540	.364	.088	.42
3/8	.675	.493	.091	.57
1/2	.840	.622	.109	.85
3/4	1.050	.824	.113	1.13
1	1.315	1.049	.133	1.68
1 1/4	1.660	1.380	.140	2.27
1 1/2	1.900	1.610	.145	2.72
2	2.375	2.067	.154	3.65
2 1/2	2.875	2.469	.203	5.79
3	3.500	3.068	.216	7.58
3 1/2	4.000	3.548	.226	9.11
4	4.500	4.026	.237	10.79
5	5.563	5.047	.258	14.62
6	6.625	6.065	.280	18.97
8	8.625	7.981	.322	28.55
10	10.750	10.020	.365	40.48
12	12.750	11.838	.406	53.56

Extra Heavy Black Pipe P.E.
Schedule 80

Size Inches	Outside Diameter	Inside Diameter	Wall Thickness	LBS. Per Ft.
1/8	.405	.215	.095	.31
1/4	.540	.302	.119	.54
3/8	.675	.423	.126	.73
1/2	.840	.546	.147	1.09
3/4	1.050	.742	.154	1.47
1	1.315	.957	.179	2.17
1 1/4	1.660	1.278	.191	3.00
1 1/2	1.900	1.500	.200	3.63
2	2.375	1.939	.218	5.02
2 1/2	2.875	2.323	.276	7.66
3	3.500	2.900	.300	10.25
3 1/2	4.000	3.364	.318	12.51
4	4.500	3.826	.337	14.98
5	5.563	4.813	.375	20.78
6	6.625	5.761	.432	28.57
8	8.625	7.625	.500	43.39

PIPE

Aluminium

Pipe
 6061 & 6063 Schedule 40
 ASTM B221, ASTM B429, AMS-QQ-A-200/8
 20' Lengths

Size (In.)	O.D.	I.D.	Average wall	Approx. WT./ FT.
.250	.540	.362	.088	.059
.500	.840	.622	.109	.294
.750	1.050	.824	.113	.391
1.000	1.315	1.049	.133	.581
1.250	1.660	1.380	.140	.786
1.500	1.900	1.610	.145	.939
2.000	2.375	2.067	.154	1.264
2.500	2.875	2.469	.203	2.004
3.000	3.5000	3.068	.216	2.621
3.500	4.000	3.548	.226	3.152
4.000	4.500	4.026	.237	3.733